


HDPE








PRESSURE PIPING SYSTEM
DRAINAGE & SEWERAGE PIPING
CABLE DUCT & SUB DUCT



NIC Products



HDPE PRESSURE PIPING SYSTEM

HDPE pipes have been used extensively for drinking water distribution throughout Europe for over 40 years and have proven to be safe and reliable for this application. PE pipe is generally resistant to the chemicals commonly used for water treatment and disinfection. HDPE PE 100 is an exciting material, being used for the manufacture of "NIC HDPE" pipes suitable for following applications.

- Civil engineering: Used for portable water, normal water supply, drainage pipeline, natural gas, heating and cooling system pipe lines, closed loop refrigeration and house cooling system, sewerage treatment plants, subsoil drainage pipes, firewatermains, house connection and plumbing.
- Oil field:Usedforcrudecollecting,sewagedisposal,crudetransportation,finishe
 dpetroleumconveyance, transportation of polymer solution to wells etc. It is
 especially suitable for transportation of mediums of oil, gas, and water with
 high sulfur content. Also best suitable for sea water intake pipes.
- Chemical industry: Applicable to acid, alkali & salt manufacture, petrochemical industry, chemical fertilizer production, pesticide production & pharmacy, etc for process tubing & drainage pipelines to convey corrosive mediums.
- 4. Ship building: Used for living pipeline system, structural & waste water pipeline.
- 5. Coal mines: Used for transportation of coal-water slurries, coal bed gas & ash, etc.
- 6. Electrical engineering: Fiber optic cable ducts, inner ducts, electrical conduits, etc.
- 7. Agriculture: Water supply and drainage pipes, Drip irrigation system, Bore well liners.
- 8. Others: metallurgical industry, food industry, compressed air pipes, etc.

TECHNICAL DATA OF PE (100)

No	Description	Value	Unit	Standard
1	Minimum Required MRS	10.0	N/mm²	PE 100
2	Density (black compound) (ρ)	940 - 960	kg/m³	ISO1183 , ISO 1872-2B
3	Melt Flow Rate(MFR) (190 °C, 2.16 kg)	< 0.15	g/10min	ISO 1133
4	Tensile Strength at yield (50mm/min)	≥ 21	MPa	ISO 527 -2
5	Elongation at break (ε)	> 350	%	ISO 527 -2
6	Hardness by shore D	≥ 60	Share D	ISO 868
7	Carbon Black Content	≥ 2 %	%	ASTM D 1603
8	Thermal Stability @ 200 °C	≥ 20	Minutes	EN 728
9	Resistance to liquid chemicals	112	Days	ISO 4433
10	Resistance to rapid crack propagation	Crack arrest	-	ISO 13477

- Service life of more than 100 years.
- Superior resistance to most of chemicals and acids.
- Virtually non degradable with living organism.
- · Most suitable material to use with sea water.
- · Smooth inner surface offers least friction compared to other pipes.
- 100% leak proof joints with butt welding of pipes & fittings.
- Can be recycled 100%.
- Economical and easy to install due to light weight.
- Can be produced in longer lengths reducing joints and cost of installation.
- Due to resistance against crack propagation HDPE pipes are suitable for Natural Gas.

APPLICABLE STANDARDS:

Standard	Title
DIN 8074 & 8075	Dimensions and quality requirement.
ISO 4427	Polyethylene pipes for water supply
ISO 4437	Buried Polyethylene pipes for the supply of gaseous fuels.
EN 1519	Polyethylene pipes for soil and waste discharge within the building structure.
ASTM D 570	Standard Test Method for Water Absorption of Plastics
ASTM D 638	Standard Test Method for Tensile Properties of Plastics
DIN 16874	Polyethylene pipes and fittings for cable ducting.
BS EN ISO 9001	Quality standard for manufacturing.
EN 12666	Plastics piping systems for non-pressure underground drainage and sewerage (PE)
EN 12201	Plastics piping systems for water supply, and for drainage and sewerage under pressure (PE)

"NIC HDPE" Pipes made from (PE 100) as per ISO 4427 DIN 8074 / 8075

Nominal Pressure at 20 °C	PN 4	PN 6*	PN 6.3	PN 10	PN 12.5	PN 16	PN 20	PN 25
SDR	SDR 41	SDR 27.6	SDR 26	SDR 17	SDR 13.6	SDR 11	SDR 9	SDR 7.4
DN (Outer dia) mm	Thickness mm							
20						2.0	2.3	3.0
25					2.0	2.3	3.0	3.5
32				2.0	2.4	3.0	3.6	4.4
40			1.8	2.4	3.0	3.7	4.5	5.5
50		1.8	2.0	3.0	3.7	4.6	5.6	6.9
63		2.4	2.5	3.8	4.7	5.8	7.1	8.6
75	1.9	2.7	2.9	4.5	5.6	6.8	8.4	10.3
90	2.2	3.3	3.5	5.4	6.7	8.2	10.1	12.3
110	2.7	4.0	4.2	6.6	8.1	10.0	12.3	15.1
125	3.1	4.5	4.8	7.4	9.2	11.4	14.0	17.1
160	4.0	5.8	6.2	9.5	11.8	14.6	17.9	21.9
200	4.9	7.2	7.7	11.9	14.7	18.2	22.4	27.4
225	5.5	8.2	8.6	13.4	16.6	20.5	25.2	30.8
250	6.2	9.1	9.6	14.8	18.4	22.7	27.9	34.2
315	7.7	11.4	12.1	18.7	23.2	28.6	35.2	43.1
355	8.7	12.9	13.6	21.1	26.1	32.2	39.7	48.5
400	9.8	14.5	15.3	23.7	29.4	36.3	44.7	54.7
450	11.0	16.3	17.2	26.7	33.1	40.9	50.3	61.5
500	12.3	18.1	19.1	29.7	36.8	45.4	55.8	68.3
560	13.7	20.3	21.4	33.2	41.2	50.8	62.5	
630	15.4	22.8	24.1	37.4	46.3	57.2		
710	17.4	25.7	27.2	42.1	52.2	64.5		
800	19.6	29.0	30.6	47.4	58.8	72.7*		
900	22.0	32.6	34.4	53.3	66.1	81.8*		

^{*} Special sizes by National Industries Company.

Allowable working pressure bars (AS per DIN 8074:2011)

	Contino	PN 4	PN 6 *	PN 6.3	PN 10	PN 12.5	PN 16	PN 20	PN 25
Temp °C	Service Life Years	SDR 41	SDR 27.6	SDR 26	SDR 17	SDR 13.6	SDR 11	SDR 9	SDR 7.4
				Allo	wable workir	ng pressure	bars		
20	50	4.0	6.0	6.3	10.0	12.5	16.0	20.0	25.0
20	100	3.9	5.8	6.1	9.8	12.3	15.5	19.5	24.6
30	25	3.4	5.1	5.4	8.6	10.9	13.7	17.3	21.8
30	50	3.4	5.0	5.4	8.5	10.7	13.5	17.0	21.5
40	25	2.9	4.4	4.6	7.4	9.3	11.7	14.8	18.6
40	50	2.9	4.3	4.6	7.3	9.1	11.5	14.5	18.3
F0	10	2.6	3.8	4.1	6.5	8.2	10.3	13.0	16.4
50	15	2.6	3.8	4.1	6.5	8.2	10.3	13.0	16.4
60	5	2.3	3.3	3.6	5.7	7.2	9.1	11.5	14.5
70	2	2.1	3.0	3.3	5.2	6.6	8.3	10.5	13.2


^{*} Special Sizes by NIC

BUTT WELDING

ASTM D 2657, ISO 21307, ISO 12176-1


"NIC HDPE" pipes are joined by Butt Welding. Butt welding of polyethylene pipe is just a matter of melting the ends of two piping components together. If required, NIC provides equipment and technical assistance for joining of pipes.

Equipment for butt welding requires electrical power. Butt welding gives a high tensile leak proof homogeneous joint.



Butt Welding





Fabricated Fittings

HDPE DRAINAGE & SEWEAGE PIPING

"NIC HDPE" drainage & sewage pipes are produced as per international standard EN 1519, DIN 19535 & DIN 19537. It can be used inside building for residential and industrial use as follows:

- Waste pipes for domestic waste waters (Low & high Temperatures)
- · Ventilation pipes connected to waste water pipes
- Discharge of rain water inside the structure of building

"NIC HDPE" Pipes made as per EN 1519

Nominal	Outside	Pipe series S 16		Pipe series S 12.5	
Dian	neter	Wall Th	ickness	Wall Thickness	
OD mm	Tolerance	T mm	Tolerance	T mm	Tolerance
32	+0.3 -0.0	3.0	+0.5 -0.0	3.0	+0.5 -0.0
40	+0.4 -0.0	3.0	+0.5 -0.0	3.0	+0.5 -0.0
50	+0.5 -0.0	3.0	+0.5 -0.0	3.0	+0.5 -0.0
63	+0.6 -0.0	3.0	+0.5 -0.0	3.0	+0.5 -0.0
75	+0.7 -0.0	3.0	+0.5 -0.0	3.0	+0.5 -0.0
90	+0.9 -0.0	3.0	+0.5 -0.0	3.5	+0.6 -0.0
110	+1.0 -0.0	3.4	+0.6 -0.0	4.2	+0.7 -0.0
125	+1.2 -0.0	3.9	+0.6 -0.0	4.8	+0.7 -0.0
160	+1.5 -0.0	4.9	+0.7 -0.0	6.2	+0.9 -0.0
200	+1.8 -0.0	6.2	+0.9 -0.0	7.7	+1.0 -0.0
250	+2.3 -0.0	7.7	+1.0 -0.0	9.6	+1.2 -0.0
315	+2.9 -0.0	9.7	+1.2 -0.0	12.1	+1.5 -0.0

Note: Imported fittings confirming to EN 1519 are available.

HDPE CABLE DUCT & SUB DUCT

EN 61386-24, KOC & MOC Standard



Smooth wall HDPE subduct for project in Kuwait

HDPE SMOOTH WALL CABLE DUCT & SUB DUCT

Sr.	Trade Size	Duct Thickness	Outer Dia.	Inner Dia.	Coil Length
No.	mm	mm	mm	mm	
1	25	2.0	25	21	200
2	32	2.0	32	28	200
3	40	2.0	40	36	200
4	40	3.5	40	33	200
5	50	2.0	50	46	200
6	50	4.0	50	42	200
7	110	5.0	110	100	100

Note:

- a. If required, duct can be supplied with pulling rope inside.
- b. Special sizes can be manufactured on request.
- c. Subducts with internal silicon coating is available to reduce internal friction.
- d. Subduct with UV resistance can be manufactured on special request.

HDPE CORRUGATED CABLE DUCT & SUB DUCT

A. Single wall




Sr. No.	Trade Size mm	Duct Thickness mm	Outer Dia. mm	Inner Dia. mm	Coil Length m
1	20	2.1	20.8	16.5	200
2	32	3.2	34.0	27.5	200
3	40	3.9	41.8	34.0	200
4	50	4.3	53.0	44.4	200
5	60	5.0	65.0	55.0	100
6	70	5.0	75.0	65.0	100
7	100	7.2	120.0	101.0	100

Note: If required, duct can be supplied with pulling rope inside

B. Double wall (Inside smooth & outside corrugated)



Sr. No.	Trade Size mm	Duct Thickness mm	Outer Dia. mm	Inner Dia. mm	Pipe Length m
1	100	2.1	120.0	101.0	6
2	150	3.2	174.0	151.0	6
3	200	3.9	232.0	201.0	6



BENEFITS:

- 30% less friction than PVC, thus while pulling cables, it experiences less stress.
- Because of flexibility, HDPE duct eliminates need for special bends and sweeps.
- · Faster installation and reduced labor costs.
- Fewer joints-better system integrity as duct is supplied in long length coils.
- Duct can be pulled over inside outer duct for long distances with minimum elongation.
- Wide variety of colours helps in easy identification when used as multiple inner ducts.
- · High crushing strength protects cable.

APPLICABLE STANDARDS:

Standard	Title
ASTM D 570	Standard Test Method for Water Absorption of Plastics
ASTM D 638	Standard Test Method for Tensile Properties of Plastics
DIN 8074 & 8075	Dimensions and quality requirement.
BS EN ISO 9001	Quality standard for manufacturing.
MOC, Kuwait	Special requirements.







Sales Outlet

Our Division at Abyat Showroom

Shuwaikh Industrial Area Canada Dry Street Abyat Showroom Contact: 1848000

> Working Hours*: Saturday - Friday 8:00am - 10:00pm



Headquarter Shuwaikh

South Shuwaikh intersection of Jahra Road and the Airport Road, Next to the Red Crescent Society.

Tel: 24642100

Kuwait Hotline: 1844555

Working Hours*:

Sunday - Thursday 7:30am - 3:00pm



Sulaibiya

Tel: 24642200

Working Hours*: Saturday - Thursday 7:30am - 3:00pm



Western Industrial Shuaiba

Tel: 24642300 Ceramics Factory: 23262714/10

Working Hours*: Saturday - Thursday 7:30am - 3:00pm

Ceramics Showroom

Industrial Shuwaikh Humaidhi Complex Opposite to Bin Nisf Co. Tel: 24950871/2 Factory: 23262714/10

> Working Hours*: Saturday - Thursday 9:00am - 9:00pm



Industrial Shuwaikh Showroom

Industrial Shuwaikh2 Block1 - Area 92 Al-Zaben Complex Shops: 12,13,14 Tel.: 24642101/2/3/4/9 Fax: 24642110

Fax : 24642110

Working Hours*: Saturday - Thursday 7:00am-9:00pm

For any sales inquiry: Fax: +965 24642063 - Email: sales@nicbm.com

* Working hours are subject to change according to holidays and occasions













